

## FORTICO 2C NATURAL

2 components, PU waterborne finish for parquet floors subject to heavy traffic. Fortico 2C is extremely scratch-resistant and does not burnish. Fortico 2C NATURAL has anti-slip properties and is easy to apply without overlaps or roller imprints. FORTICO 2C NATURAL provides an invisible, natural finish.

- » Provides an invisible finish.
- » Extremely scratch resistant thanks to anti-scratch technology.
- » High wear resistance.
- » Doesn't burnish.

### TECHNICAL DATA

**Product type**  
waterborne

**Cleaning**  
Water

**Mixing ratio**  
100/10

**Gloss level**  
Natural <10

**Viscosity**  
+/-20 sec - DIN 4mm

**Solids content**  
+/- 32%

**Packaging**  
4 x 5 L/ 4 x 500 ml Hardener  
6 X 1 L/ 6 x 100 ml Hardener

**Coverage**  
+/- 10 - 12 m<sup>2</sup>/liter per coat  
100-125 sq.ft./L per coat  
380 - 470 sq.ft./gal per coat


**Drying times**  
Dust dry: after 20 to 30 minutes  
Sandable: after 4 to 6 hours  
Lightly walkable: after 24 hours  
Fully cured: After +/- 7 days

**Sanding grit**  
P 120-150

**Storage/transport**  
between 5°C and 25°C

**Potlife**  
+/- 3 hours after adding the hardener

**Disposal**  
Dispose of residue and empty packaging in accordance with local ordinances.



### PREPARATION

Make sure that all old finish coats are completely removed and that the wood is free from dust and other dirt. Sanding using the correct method: deep sanding with 60-80-100 grit then sanding with 100 grit. Can be used on sanded, planed, and brushed wood. For a lighter finish, WOODLOOK PLUS can be used as a primer first.

### APPLICATION

Use FORTICO 2C as a primer and finishing coat. Mix the waterborne finish with the hardener at 10 to 1 (10%). Let the product settle for 15 minutes. Apply the product in 3 layers with a brush or roller.

First layer: apply ca. 7.50 - 9.50 g/sq.ft and let dry for +/- 4 hours.  
Second layer: apply ca. 7.50 - 9.50 g/sq.ft in the same manner as the first layer and let dry for +/- 6 hours.

Afterwards intermediate sanding with grain 180-220, make it dust-free and apply the third layer at ca. 7.50 - 9.50 g/sq.ft.

### CAUTION

Dust dry: after 20 to 30 minutes  
Sandable: after 4 or 6 hours  
Lightly walkable: after 24 hours

The drying times strongly depend on the amount applied, the surrounding temperature, the humidity and ventilation.

### FINISHING

FORTICO can be used as a primer and finishing coat.

### MAINTENANCE

Regular maintenance with Hard Floor Fresh Ciranova®. For periodic maintenance, use UNICARE X-MATT for natural & matt finish and Hard Floor Polish for the satin finish. Hard Floor Cleaner Ciranova® is used for cleaning highly soiled floors and to remove old layers of polish.

### IMPORTANT INFORMATION ⚠

Only use corrosion-resistant materials. Clean all materials with water immediately afterwards. For industrial applications, the Ciranova® technical service should be consulted. Water-based products can develop skins after contact with air. Filter beforehand, if necessary.