

HARDWAXOIL MAGIC

PRODUCT DESCRIPTION:

Flooring oil suitable for oil finishing of wooden floors. Good filling properties, natural colour, good chemical and mechanical resistance. Does not shine and is very matt. The durability can be improved by adding the hardener UA 5% (optional).

RANGE OF APPLICATION:

Industrial application for Wood Flooring and wood panels. Only for interior use

CERTIFICATES/LABELS:

CpdH / A+ (Fr) / AgBB / Belgian indoor Pass

TECHNICAL DATA

extra component:	HARDENER UA
mixing ratio:	100:5
pot-life:	CA 6 HRS
density:	depending on colour
viscosity:	ca 50" DIN 4 (at 20°C)
colors:	8 colors available
solid content:	ca 47%
gloss:	Matt - Satin
thinner:	Oil Retarder
coverage per coat:	ca 20 - 25g/m ²
Coverage USA per coat:	ca 2 - 2.5g/ft ²
drying:	6 - 12 hrs depending on the color

APPLICATION MATERIAL



PACKING

5L - 25L

APPLICATION

preparation substrate: Prepare the wood according the rules of the art and remove the sanding dust carefully

processing: Mix the oil with the hardener (100:5) and let the product rest for about 10 minutes.
When needed color the wood with stains from Ciranova Industrial Finishes.
can be applied with a roller coater and buf after with a white or beige pad. Use brushes to remove the marks of the buffing pads.

PROTECTION

Always end with a clear Oil on top.

MAINTENANCE

Please consult the maintenance programm from Ciranova.

IMPORTANT INFORMATION

Used cloths or pads should be plunged in water because of the danger of spontaneous combustion. We recommend Hardwaxoil Magic Natural as topcoat on the pigmented Hardwaxoils.
Colored Hardwaxoils should always be tested before treating the entire surface.
Used sanding grain, type of wood, may affect the final color.

SHELF-LIFE

In well-closed and original packing: minimum 24 months

WAREHOUSING

by 10 - 40 °C

CLEANING

COMBI CLEANER 2879

ATTENTION ⚠

"All tests and application methods are done with the above-mentioned Debal Coatings components. We are not responsible for application with other materials, unless written agreement from Debal Coatings"