

## UV FLOORING SEALER MATT

### PRODUCT DESCRIPTION:

This UV flooring clear sealer matt is a UV curing product and reach a high level of transparency / matt pore' s.  
Used in open pore UV Wood flooring systems.

### RANGE OF APPLICATION:

Industrial application for Wood Flooring and wood panels.  
Only for interior use

### CERTIFICATES/LABELS:

DIN 68861 -1B  
DIN 53160

### TECHNICAL DATA

<b>extra component:</b>	-
<b>mixing ratio:</b>	-
<b>pot-life:</b>	-
<b>density:</b>	1,21 KG/L
<b>viscosity:</b>	35-45 s / 6mm @ 20 °C
<b>colors:</b>	clear
<b>solid content:</b>	ca 97%
<b>gloss:</b>	matt
<b>thinner:</b>	-
<b>coverage per coat:</b>	ca 20 -25g/m <sup>2</sup>
<b>Coverage USA per coat:</b>	ca 2 - 2.5g/ft <sup>2</sup>
<b>drying:</b>	UV Curing

### APPLICATION MATERIAL



### PACKING

20kg

### APPLICATION

**preparation substrate:** Prepare the wood according the rules of the art and remove the sanding dust carefully

### processing:

Stirr well before use  
 · Apply +/- 15 – 30 g/m<sup>2</sup>.  
 · UV Flooring sealer matt is intend to use as next layer on the UV Hydroprimer clear 7893.  
 · Cure by UV lamps (1 lamp Hg 80W -5-10 m beltspeed)  
 · Topcoat: UV Topcoat 7894 AS GL 10.  
 · Follow the corresponding technical data sheet.

### PROTECTION

UV Lacquer system

### IMPORTANT INFORMATION

Protect open drums from UV light.  
 · Close carefully drums after using.  
 · Check adhesion of the system on regular bases, change settings of the UV lamps when necessary.  
 · For industrial use only

### SHELF-LIFE

In well-closed and original packing: minimum 9 months

### WAREHOUSING

by 10 – 40 °C

### CLEANING

COMBI CLEANER 2879

### ATTENTION ⚠

"All tests and application methods are done with the above-mentioned Debal Coatings components.  
We are not responsible for application with other materials, unless written agreement from Debal Coatings"