

## UV TOPCOAT AS

### PRODUCT DESCRIPTION:

High Quality UV curing topcoat with good anti scratch properties.

Reach a high level of transparent, smooth matt surface. Used in open / closed pore systems for UV Wood flooring systems.

### RANGE OF APPLICATION:

Industrial application for Wood Flooring and wood panels. Only for interior use

### CERTIFICATES/LABELS:

DIN 68861-1B Chemical resistance

DIN 53160

### TECHNICAL DATA

<b>extra component:</b>	-
<b>mixing ratio:</b>	-
<b>pot-life:</b>	-
<b>density:</b>	1,15 KG/L
<b>viscosity:</b>	18-25 s / 6mm @ 20 °C
<b>colors:</b>	clear
<b>solid content:</b>	0,97
<b>gloss:</b>	Ca 10 GU at 60°
<b>thinner:</b>	-
<b>coverage per coat:</b>	ca 160 m <sup>2</sup> /kg per coat
<b>Coverage USA per coat:</b>	ca 1600ft <sup>2</sup> /kg per coat
<b>drying:</b>	UV Curing

### APPLICATION MATERIAL



### PACKING

20kg

### APPLICATION

#### preparation substrate:

-

#### processing:

- Stirr well before use
- To avoid adhesion issues, sand the UV sealer thoroughly and apply UV Topcoat 7894 within 12Hours.
- Apply +/- 2 X 6 gr/M2
- Cure by UV lamps (1 lamp Hg 80W -5-10 m beltspeed)
- Follow the corresponding technical data sheet.

### PROTECTION

Please consult the maintenance programm from Ciranova.

### IMPORTANT INFORMATION

- Protect open drums from UV light.
- Close carefully drums after using.
  - Check adhesion of the system on regular bases, change settings of the UV lamps when necessary.
  - Temperature of use 15-40°C
  - For industrial use only

### SHELF-LIFE

In well-closed and original packing: minimum 9 months

### WAREHOUSING

by 10 – 40 °C

### CLEANING

COMBI CLEANER 2879

#### ATTENTION ⚠

"All tests and application methods are done with the above-mentioned Debal Coatings components. We are not responsible for application with other materials, unless written agreement from Debal Coatings"