

## VINTAGE F VINTAGE X

### PRODUCT DESCRIPTION:

VINTAGE X and VINTAGE F age the wood by oxidation for tannin containing wood species. In combination with bleaching you can obtain a grayish-aged look.

### RANGE OF APPLICATION:

Industrial application for Wood Flooring and wood panels.  
Only for interior use

### TECHNICAL DATA

<b>extra component:</b>	-
<b>mixing ratio:</b>	-
<b>pot-life:</b>	-
<b>density:</b>	+/- 1.00 KG/L
<b>viscosity:</b>	as water
<b>colors:</b>	yellow - orange
<b>solid content:</b>	-
<b>gloss:</b>	-
<b>thinner:</b>	-
<b>coverage per coat:</b>	ca 50g/m <sup>2</sup>
<b>Coverage USA per coat:</b>	ca 5 g/ft <sup>2</sup>
<b>drying:</b>	Reaction time: minimum 12 hrs

### APPLICATION MATERIAL



### PACKING

5lt - 25lt

### APPLICATION

**preparation substrate:** Prepare the wood according the rules of the art and remove the sanding dust carefully

**processing:**

- Stir before use and mix separate batches to ensure the color consistency.
- Do not work out of the container.
- Use foam brush, synthetic brush or sprayer and apply a generous coat around 50 - 60g/m<sup>2</sup>
- even out in the direction of the grain.
- After complete reaction time, smoothen the surface with a pad or wire brush.
- For an additional bleaching step, please contact our technical dept.

### PROTECTION

Preferably finish with an oil to protect the wood and the color. Alternatively a color locking primer can be used, often in combination with an extra matt topcoat (UV 680-007403 – HWO titan 650-008091) for a natural looking finish.

### IMPORTANT INFORMATION

- Respect reaction time.
- The final color depends on the type of wood, sanding, wood preparation and the applied quantity. For this reason its always recommended to make a test first before starting production.
- Only use stainless material.
- immediately after use.

### SHELF-LIFE

In well-closed and original packing: minimum 12 months

### WAREHOUSING

by 10 – 40 °C

### CLEANING

HYDRO CLEANER 7984

### ATTENTION ⚠

"All tests and application methods are done with the above-mentioned Debal Coatings components. We are not responsible for application with other materials, unless written agreement from Debal Coatings"