

FORTICO 2C SATIN MATT - NATURAL

Aqueous-phase, two-component PU parquet varnish for parquet and heavy-duty floors. FORTICO 2C has excellent chemical and mechanical resistance. Easy application with no overlaps or roller marks. FORTICO 2C has been specially developed for high-traffic parquet areas such as commercial spaces, hotels, restaurants, etc.

- » Extremely scratch-resistant thanks to anti-scratch technology.
- » High wear resistance.
- » Does not glare.

TECHNICAL DATA

Product type

water-based

Cleaning tools

water

Mixing ratio

100/10

Gloss level

Matt 10-15; Satin 35-50; Natural <5

Viscosity

+/-25 sec - DIN 4mm

Packaging

6 x 1 l / 100 ml hardener

4 x 5 l / 500 ml hardener

Coverage

10-12m²/litre per coat

Drying/reaction time

Touch-dry after 2 hours

Can be sanded after: 3 to 5 hours

Light traffic after: 24 hours

Fully cured: after 7-10 days

Abrasive grain

P 120-150

Transport

between 5°C and 25°C

Pot life

+/- 3 hours after adding hardener

Waste

Dispose of residues and empty packaging in accordance with local regulations.



PRELIMINARY TREATMENT

Make sure that all old finishing coats are removed and that the floor is clean and free of residues. Sand using the correct method: deep sanding with 60-80-100 grit, followed by abrasive sanding with 100 grit. Can be used on planed, sanded and brushed wood. For a lighter, more natural finish, you can first use FORTICO 2C NATURAL as a base coat.

For floors with underfloor heating, exotic woods and cork, we recommend FORTICO SEALER as a base.

APPLICATION

Use FORTICO 2 C as both base and top coat. Mix the varnish with the hardener in a 10:1 ratio before use. Leave the product to stand for 15 minutes. Pot-life is 3 hours, after mixing with hardener.

Apply the 3 coats of the product using a spalter brush or roller (8 mm microfibre). First coat: apply approx. 10 m²/l and allow to dry for +/- 3 hours.

Second coat: apply approximately 10 m²/l in the same way as the first coat and allow to dry for +/- 3 hours. Then sand with sand paper (P120-150), remove dust and apply the third coat covering approximately 10 m²/L.

DRYING TIME

Light traffic after 24 hours.

Fully cured after 7 to 10 days.

Drying times are highly dependent on the quantity applied, ambient temperature, humidity and ventilation.

FURTHER TREATMENT

FORTICO 2C can be used as a base and a top coat.

MAINTENANCE

Maintain regularly with HARD FLOOR FRESH Ciranova®. For periodic maintenance, use HARD FLOOR POLISH Ciranova® or UNICARE X-MATT Ciranova®. HARD FLOOR CLEANER Ciranova® is used to clean heavily soiled floors and remove old coats of varnish.

IMPORTANT INFORMATION

Use stainless steel/rustproof equipment only. Clean all tools and equipment with water immediately after use. For industrial applications, please contact the Ciranova technical service®. Water-based products can form a film on contact with air. Pre-filter the product if necessary.